



Contribution ID: 320

Type: Oral (Non-Student) / orale (non-étudiant)

Direct transfer of triplet excitons generated by singlet fission to colloidal quantum dots: A route to sensitize silicon solar cells

Wednesday 18 June 2014 14:30 (15 minutes)

Singlet exciton fission is the process in organic semiconductors by which one Coulombically-bound electron-hole pair (exciton) with net singlet spin evolves into a pair of spin-triplet excitons. Although the phenomenon has long been a curiosity in organic crystals[1], we recently demonstrated that singlet fission proceeds rapidly (80fs-400ps)[2-4] and efficiently (approaching quantitative ('200%') yield)[4-5] in thin films made from a range of organic molecules that satisfy the energetic criteria: $E_{sing} \geq 2 \cdot E_{trip}$ [4].

Critically, singlet fission is now attracting wider interest[6] because it could boost the power conversion efficiency of photovoltaic devices. Specifically, as first envisioned by Dexter[7], a blue-absorbing singlet fission material could sensitize a red-absorbing solar cell, enabling the generation of additional photocurrent from high-energy photons. However, though we have recently reported fission-based photovoltaic devices where the peak photon-to-electron conversion efficiency is greater than unity [8-9], their overall power conversion performance remains unremarkable, as they rely on immature solar technologies (e.g. organic semiconductors) for the red-absorbing cell.

Here, by detecting a characteristic magnetic field dependence using steady-state and transient spectroscopies, we demonstrate that fission-generated triplet excitons readily undergo exchange-mediated (Dexter) transfer to PbS colloidal quantum dots. Because the spin-states of the quantum dots are mixed at room temperature, this renders the fission-generated excitons emissive. Thus, we consider that longer-range Förster energy transfer may permit the direct sensitization of a conventional back-contacted silicon solar cell with an organic singlet fission material.

- [1] Swenberg, C.E., & Geacintov, N.E. **Org. Mol. Photophys.** (1973)
- [2] Wilson, M.W.B., *et al.* **J. Am. Chem. Soc.** (2011)
- [3] Wilson, M.W.B., *et al.* **J. Am. Chem. Soc.** (2013)
- [4] Yost, S.R., Lee, J., Wilson, M.W.B., *et al.*, **Nat. Chem.** (In Press)
- [5] Thompson, N.J., *et al.* **Adv. Mater.** (2013)
- [6] Smith, M.B., & Michl, J. **Annu. Rev. Phys. Chem.** (2013)
- [7] Dexter, D.L. **J. Lumin.** (1979)
- [8] Congreve, D.N., Lee, J., Thompson, N.J., *et al.* **Science** (2013)
- [9] Thompson, N.J. *et al.* **Appl. Phys. Lett.** (2013)

Authors: WILSON, Mark W.B. (Massachusetts Institute of Technology); THOMPSON, Nicholas J. (Massachusetts Institute of Technology)

Co-authors: SCHERER, Jennifer M. (Massachusetts Institute of Technology); Prof. BALDO, Marc A. (Massachusetts Institute of Technology); Prof. BAWENDI, Moungi G. (Massachusetts Institute of Technology); BISCHOF, Thomas S. (Massachusetts Institute of Technology)

Presenter: WILSON, Mark W.B. (Massachusetts Institute of Technology)

Session Classification: (W2-2) Photovoltaic and optical materials - DCMMP / - Matériaux photovoltaïques et optiques - DPMCM

Track Classification: Condensed Matter and Materials Physics / Physique de la matière condensée et matériaux (DCMMP-DPMCM)