



Canadian Association  
of Physicists

Association canadienne  
des physiciens et physiciennes

Contribution ID: 2060

Type: Oral (Non-Student) / Orale (non-étudiant(e))

## Structure and Properties of Exfoliated MoS<sub>2</sub>-Polyaniline Nanocomposites

*Tuesday 12 June 2018 15:30 (15 minutes)*

Molybdenum disulfide was produced in an exfoliated state by combining molybdic acid with an excess of thiourea at 500°C under nitrogen. Nanocomposites of the conducting polymer polyaniline (PANI) and exfoliated MoS<sub>2</sub> were then synthesized. The nanocomposites with varying percentage by weight of exfoliated MoS<sub>2</sub> were characterized using powder X-Ray diffraction, electrical conductivity measurements, Seebeck coefficient measurements, thermogravimetric analysis, scanning electron microscopy, and transmission electron microscopy. An intriguing result was seen in the conductivity data, where several of the nanocomposites containing relatively small percentages of exfoliated MoS<sub>2</sub> yielded higher conductivity overall in comparison to a sample of pure PANI. The exfoliated MoS<sub>2</sub> used in this work is highly disordered, and is expected to be predominantly the 2H polytype. This form of MoS<sub>2</sub> has very low conductivity, thus the increased conductivity of the nanocomposite suggests that PANI is most likely stabilizing MoS<sub>2</sub> in its 1T metallic form, which is higher in conductivity.

**Authors:** Ms LYLE, Erin (Department of Chemistry, U. Prince Edward Island); Dr DAHN, Douglas (Department of Physics, U. Prince Edward Island); Dr BISSESSUR, Rabin (Department of Chemistry, U. Prince Edward Island)

**Co-author:** Mr MCALLISTER, Cody (Department of Chemistry, U. Prince Edward Island)

**Presenter:** Dr DAHN, Douglas (Department of Physics, U. Prince Edward Island)

**Session Classification:** T4-4 Films, surfaces and composites (DCMMP) | Films, surfaces et composites (DPMCM)

**Track Classification:** Condensed Matter and Materials Physics / Physique de la matière condensée et matériaux (DCMMP-DPMCM)