



Contribution ID: 57

Type: Oral

## Enhanced piezoelectric properties and fatigue-free behavior of lead-free piezoelectric $x\text{BaZrO}_3\text{-(}0.85\text{-}x\text{)BaTiO}_3\text{-}0.15\text{CaTiO}_3$ ceramics

*Tuesday 29 November 2016 14:35 (15 minutes)*

Lead-free  $x\text{BaZrO}_3\text{-(}0.85\text{-}x\text{)BaTiO}_3\text{-}0.15\text{CaTiO}_3$ ;  $x = 0.00\text{-}0.20$  (xBZ) ceramics were successfully prepared using the conventional solid-state reaction method. X-ray diffraction data showed a pure-phase perovskite structure for compositions up to  $x < 0.200$ . At room temperature, x-ray diffraction patterns of ceramics with the composition range of  $0.00 \leq x < 0.10$  possess tetragonal structure. Mixed-phase coexistence of tetragonal and rhombohedral phases were found at  $0.10 \leq x \leq 0.15$  and transformed to cubic for  $x > 0.125$  according to the lowered Curie temperature. Raman scattering showed mixed phases of tetragonal and orthorhombic phases. Temperature-dependent dielectric data shows anomaly phase transitions determined by composition changes. Phase diagram was provided according to temperature-dependent dielectric data. Compositions near composition-induced phase transition provided enhanced ferroelectric and piezoelectric properties. Unipolar electric field induced strain of  $x = 0.125$  ceramic shows surprisingly high longitudinal piezoelectric coefficient ( $d_{33}^*$ ) of 2244 pm/V at relatively low electric field of 5 kV/cm. Fatigue measurement carried out on the morphotropic phase boundary composition showed a small degradation in maximum strain after 106 cycles using an applied field of 20 kV/cm at 10 Hz.

**Author:** Dr MUANGHLUA, Rangson (Faculty of Engineering, King Mongkut's Institute of Technology Ladkrabang)

**Presenter:** Dr MUANGHLUA, Rangson (Faculty of Engineering, King Mongkut's Institute of Technology Ladkrabang)

**Session Classification:** Falcon 1

**Track Classification:** Other related topics