

Influence of temperature annealing on structural and optical properties of α -MoO₃ films prepared by a spray pyrolysis method

Monday 21 May 2018 18:30 (15 minutes)

Layers of polycrystalline molybdenum trioxide (MoO₃) thin films were successfully deposited on fluorine-doped tin oxide (FTO) coated glass by a spray pyrolysis technique at the deposition temperature of 425°C for 1 hour. The prepared films were further annealed at 500 °C for 0.5, 1, 1.5, 2 and 3 hours. The effect of the annealing periods of time on their structural, morphological and optical properties was methodically investigated. The XRD results indicate that the films show high crystallinity with an orthorhombic crystal structure of α -MoO₃ phase after the post-annealing treatment. The films annealed for 1 hour exhibit the strongest (020) preferred orientation with their lattice parameters of $a = 3.939 \text{ \AA}$, $b = 13.728 \text{ \AA}$ and $c = 3.682 \text{ \AA}$. The surface morphology of the films presents rod-like particles and their sizes appear to become larger with increasing the annealing times. The values of optical band gap of the films obtained from absorbance spectra are varied in a range of 3.02-3.32 eV, depending on the annealing times.

Authors: ROSUNGNERN, Unyamanee (Kasetsart University); SUPASAI, Thidarat (Department of Materials Science, Faculty of Science, Kasetsart University, Bangkok 10900, Thailand)

Presenter: ROSUNGNERN, Unyamanee (Kasetsart University)

Session Classification: A05: Nanoscale and Surface (Poster)

Track Classification: Surface, Interface and Thin Film